**Technical Information Sheet** 

## Trade Car Paints 2k Acrylic

Units 313-317 Heath Street, Smethwick, West Midlands, B66 2QY TEL: 0121 558 6193 Fax:0121 565 1559

## APPLICATION DATA

	Mixing ratio	: 2:1 (2K/N 3:1 (HS Har	/IS Hardeners) deners)	
S	Application- Viscosity	Air Spray Pressure tai		
	Gravity Suction HVLP/L Pressur Airless	feed feed VLP	Dray nozzle (mm) 1.3-1.5 1.6-1.8 1.3-1.5 1.0-1.4 0.007-0.009"/40°	Pressure (bar) 3.5-4.5 3.5-4.5 See manufacturer info 4.0-5.0 160-200
	Spray coats/ Coat thickness	: 2-3 40-60 μn	n	
<u>/†/†/</u>	Flash-off time	: 10-15 mi	in	
	Drying :	<u>20°C</u> 8 h	<u>60°C</u> 30 min	
	Potlife	: Ca. 5 h/2	20°C	

The technical data in these publications are based on our present knowledge and give you an idea of the various applications without obligations. [mei-05]