



Loctite UK Ltd

Watchmead, Welwyn Garden City
Hertfordshire. AL7 1JB
Tel +44 (0)1707 358 888
Fax +44 (0)1707 358 910

Technical Data Sheet

Product: Stonechip Protect

(PP 300/1)

PRODUCT DESCRIPTION

A tough, alkyd based plastic coating for protection against stonechip damage. Dries to a textured, "orange peel" appearance, which can be left unpainted or matched to the original bodywork.

Typical applications

For protection against stonechip damage on motor vehicle spoilers, sills etc.

Properties of uncured material

Binder	Alkyd
Solvent	Xylene
Appearance	Black or White liquid
Density @ 25 °C, kg/dm ³	1.35 (Black), 1.25 (White)
Dry content, % by volume	45
Dry content, % by weight	60
Viscosity, KU	~80

Drying

Drying

Stonechip Protect will dry in approx. 2 hours at +23 °C and in 30 minutes at +80°C. Low temperature and thick layers will prolong drying time.

Application data

Recommended layer, µm	350-500
Airline gun pressure, Bar	~4
Coverage m ² /dm ³	1.5-3

Chemical resistance

Protects against stonechip, water, salt etc. Resistant to degreasing agents.

General information

Directions for use

Can be applied direct to flatted surfaces if paintwork is in good condition. Use suitable primer on bare metal.

Use a brush, roller, airline gun or aerosol to apply the product. Can be thinned sparingly with xylene.

Cleaning

Clean tools with xylene or thinner after use.

Storage

The product has a storage life of 1 year from date of manufacture. For maximum storage life store in a cool place.

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Loctite Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Loctite Corporation's products. Loctite Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a licence under any Loctite Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

NOT FOR PRODUCT SPECIFICATIONS

THE TECHNICAL DATA CONTAINED HEREIN ARE INTENDED AS REFERENCE ONLY.

PLEASE CONTACT LOCTITE SWEDEN AB R & D DEPARTMENT FOR ASSISTANCE AND RECOMMENDATIONS FOR THIS PRODUCT.

GÖTEBORG +46 (0)31 750 54 90