

Trade Car Paints
313 – 317 Heath Street
Smethwick
West Midlands
B66 2QY

Tel: 0121 558 6191

website: www.tradecarpaints.co.uk

PRODUCT SPECIFICATION SHEET

TWO PACK EPOXY PAINT FLOOR PAINT

High performance coating having excellent water and chemical resistance. These materials are supplied in pre-weighted packs as base and hardener. The two components should be mixed thoroughly before use, only enough should be prepared for use that can be used within the pot life, and all application equipment should be cleaned within this time.

PREPERATION

Ensure surface to be painted is sound, clean, dry and free from dust and other contaminations including loose flaking paint. It is recommended to use an appropriate sealer on new or bare concrete. (P70 see relevant technical data sheet) Existing floor coatings should not be over coated without first testing a small area for compatibility.

VISCOSITY: 2.5 Poise / 20'C

THINNERS: T7003 (T3)

APPLICATION Spray or brush

OVERCOATING: Within 3 days

DRYING TIME: Dependent on temperature. The following are given as a guide at 17'C they may be doubled at 7'C.
Ready for light pedestrians traffic after 24 hours, other after full cure time.

FULL CURE 7 DAYS

